



COR-TEN AZP® Raw
SR .32 TE .89 SRI 34



COR-TEN AZP® Robust
SR .32 TE .85 SRI 32

If your next architectural project requires the look of an aged or weathered roofing or cladding product, the Weathered Metal Series™ will give your project the distinctive aged appearance and the rich, classic character that until now, only time — and the elements — could provide.

AGED TO PERFECTION

WEATHERED METAL SERIES™

With age comes a classic and sublime beauty, and note that look is available for your next roofing or cladding project. Now, with our unique, Weathered Metal Series™, you have a choice of two, distinct stages of aging — moderately weathered Raw and more heavily weathered Robust. Each pattern is carefully crafted and engineered to give your next roofing or cladding project the authentic look of timelessness.

The Weathered Metal Series™ is a fluoropolymer coating system that uses cool pigment technology that is applied over GALVALUME® coated steel sheet.

Now you have the power and the freedom to design in a way that before now, only time and Mother Nature could.

The colors shown are for sample purposes only. This is a unique appearance coating that needs to be seen. Please request an actual color sample from our color experts.

PERFORMANCE PROPERTIES

WEATHERED METAL SERIES™

Typical Test Results*

Performance	Test Method	GALVALUME® Coated Steel Sheet
Adhesion	ASTM D3359	No loss of adhesion
Flexibility	ASTM D4145	1T to 3T, no loss of adhesion
Pencil Hardness	ASTM D3363	HB Minimum
Reverse Impact	ASTM D2794	3x metal thickness, NTO
Abrasion Resistance	ASTM D968	65 ± 10 liters per mil
Specular Gloss	ASTM D523	Less than 25 to 60°
Salt Spray	ASTM B117	1,000 hours – 1/16" max creep from scribe
Humidity	ASTM D2247	2,000 hours – no field blisters
Dew Cycle Weathermeter	ASTM D3361	1,000 hours – Chalk Rating no less than 8

*Results may vary depending on substrate and gauge.

The information contained herein is based on tests and reports considered reliable, but is presented without guarantee or responsibility as to the applicability or correctness of this information or the suitability of our products, whether used singly or in combination with other products.

At A Glance

Material	.0236
Material Thickness*	24 ga
Material Width	48.25"

Weathered Metal Series™ COR-TEN® and COR-TEN® AZP® are registered trademarks of United States Steel Corporation.

*General Guidelines – Dependent upon alloy, temper and yield strength.

GALVALUME® is an internationally registered trademark of BIEC International Inc. and some of its licensed producers.